



DATA SHEET EP80PF

General properties

Standard	ASTM
Indicative working temperature	-50°C/+150°C
Color	BLACK
Chemical resistance	<input type="checkbox"/> Oil Free <input checked="" type="checkbox"/> Phthalate Free <input checked="" type="checkbox"/> Reach&RoHs2.0

Properties

	Method	Unit	Required value	value
Hardness	ASTM D 2240	IRHD		79
Tensile strength	ASTM D 412/C	N/mm2(Mpa)		14.68
Elongation at break	ASTM D 412/C	%		158
Tear strength	ASTM D 624/B	N/mm		38.02
Specific gravity	ASTM D 1817	g/cm3		1.174
Low temperature test-TR10	ASTM D 1329	°C		
Low temperature test-Brittleness	ASTM D 746	°C		
Compression Set after deformation of 25%, 22 hours at 150°C	ASTM D 395/B	%		10.4

Ageing

Fluid	Time(h)	Temperature °C	Tensile %	Elongation %	Hardness Pts	Volume %	Weight %
Air	70	150	-7	-3	+2	-0.7	

Approval

ACS

KTW

SPEC:

Date : 29/11/2007

Edit date: 23/04/2021

Index:

Author:

SVHC = Substance of Very High Concern according to regulation REACH 1907/2006

These data are for information only.

They can be modified at any moment without notice.

Values indicated above are based on tests conducted on laboratory samples.

Values on finished parts can be different depending on shape, curing parameters etc