



DATA SHEET EP90PF

General properties

Standard	ASTM
Indicative working temperature	-40°C/+150°C
Color	BLACK
Chemical resistance	<input checked="" type="checkbox"/> Oil Free <input checked="" type="checkbox"/> Phthalate Free <input checked="" type="checkbox"/> Reach&RoHs2.0

Properties

	Method	Unit	Required value	value
Hardness	ASTM D 1415	IRHD	90+/-5	85
Tensile strength	ASTM D 412/C	N/mm2(Mpa)		13.51
Elongation at break	ASTM D 412/C	%		116
Tear strength	ASTM D 624/B	N/mm		41.16
Specific gravity	ASTM D 1817	g/cm3		1.221
Low temperature test-TR10	ASTM D 1329	°C		
Low temperature test-Brittleness	ASTM D 746	°C		
Compression Set after deformation of 25%, 22 hours at 125°C	ASTM D 395/B	%		8.2
Compression Set after deformation of 25%, 70 hours at 100°C				13.7

Ageing

Fluid	Time(h)	Temperature °C	Tensile %	Elongation %	Hardness Pts	Volume %	Weight %
Air	70	125	-2	-2	+1	-0.3	
Water	70	100	-5	+4	-4	+5	

Low temperature resistance ASTM D2137,Method A, 3 min at -40 °C PASS

Approval

KTW.W270

ACS

SPEC: SPEC: M2CA910A25B44B35EA14G21

Date : 16/03/2010

Edit date: 23/02/2021

Index:

Author:

SVHC = Substance of Very High Concern according to regulation REACH 1907/2006

These data are for information only.

They can be modified at any moment without notice.

Values indicated above are based on tests conducted on laboratory samples.

Values on finished parts can be different depending on shape, curing parameters etc