



DATA SHEET SE90F

General properties

Standard	ASTM
Indicative working temperature	-60°C/+180°C
Color	BLACK
Chemical resistance	<input type="checkbox"/> Oil Free <input checked="" type="checkbox"/> Phthalate Free <input checked="" type="checkbox"/> Reach&RoHs2.0

Properties

	Method	Unit	Required value	value
Hardness	ASTM D 2240	Shore A		90
Tensile strength	ASTM D 412/C	N/mm2(Mpa)		5.7
Elongation at break	ASTM D 412/C	%		103
Tear strength	ASTM D 624/B	N/mm		20.58
Specific gravity	ASTM D 1817	g/cm3		1.276
Low temperature test-TR10	ASTM D 1329	°C		
Low temperature test-Brittleness	ASTM D 746	°C		
Compression Set after deformation of 25%, 22 hours at 175°C	ASTM D 395/B	%		14

Ageing

Fluid	Time(h)	Temperature °C	Tensile %	Elongation %	Hardness Pts	Volume %	Weight %
Air	70	225	-19	-36	+4	-2	
ASTM1	70	150	-3	-18	-3	+5	
ASTM3	70	150	+12	-6	-23	+33	
Water	70	100	-5	-9	0	0	

Approval

SPEC:
Date : 06/03/2008
Edit date: 10/01/2022
Index:
Author:

SVHC = Substance of Very High Concern according to regulation REACH 1907/2006
Material Silicone are confirm with Reach except 190(D4)、184(D5)、187(D6).
These data are for information only.
They can be modified at any moment without notice.
Values indicated above are based on tests conducted on laboratory samples.
Values on finished parts can be different depending on shape, curing parameters etc