



DATA SHEET ACM70LT

General properties

Standard	ASTM
Indicative working temperature	-35°C/+150°C
Color	BLACK
Chemical resistance	<input checked="" type="checkbox"/> Oil Free <input checked="" type="checkbox"/> Phthalate Free <input checked="" type="checkbox"/> Reach&RoHs2.0

Properties

	Method	Unit	Required value	value
Hardness	ASTM D 1514	IRHD		73
Tensile strength	ASTM D 412/C	N/mm2(Mpa)		9.95
Elongation at break	ASTM D 412/C	%		106
Tear strength	ASTM D 624/B	N/mm		17.64
Specific gravity	ASTM D 1817	g/cm3		1.325
Low temperature resistance	ASTM D 2137	°C		-31
Low temperature test-Brittleness	ASTM D 746	°C		
Compression Set after deformation of 25%, 22 hours at 150°C	ASTM D 395/B	%		

Ageing

Fluid	Time(h)	Temperature °C	Tensile %	Elongation %	Hardness Pts	Volume %	Weight %
-------	---------	----------------	-----------	--------------	--------------	----------	----------

Approval

SPEC:
Date : 16/09/2008
Edit date: 09/01/2022
Index:
Author:

SVHC = Substance of Very High Concern according to regulation REACH 1907/2006
These data are for information only.
They can be modified at any moment without notice.
Values indicated above are based on tests conducted on laboratory samples.
Values on finished parts can be different depending on shape, curing parameters etc